

## SCUOLA INTERNAZIONALE SUPERIORE DI STUDI AVANZATI

SISSA Digital Library

Chemically Cross-Linked Carbon Nanotube Films Engineered to Control Neuronal Signaling

Original

Chemically Cross-Linked Carbon Nanotube Films Engineered to Control Neuronal Signaling / Barrejón, Myriam; Rauti, Rossana; Ballerini, Laura; Prato, Maurizio. - In: ACS NANO. - ISSN 1936-0851. - 13:8(2019), pp. 8879-8889. [10.1021/acsnano.9b02429]

Availability:

This version is available at: 20.500.11767/98816 since: 2019-07-23T09:44:01Z

Publisher:

Published DOI:10.1021/acsnano.9b02429

Terms of use:

Testo definito dall'ateneo relativo alle clausole di concessione d'uso

Publisher copyright

note finali coverpage

(Article begins on next page)



Article

## Chemically Cross-Linked Carbon Nanotube Films Engineered to Control Neuronal Signaling

Myriam Barrejón, Rossana Rauti, Laura Ballerini, and Maurizio Prato

ACS Nano, Just Accepted Manuscript • DOI: 10.1021/acsnano.9b02429 • Publication Date (Web): 22 Jul 2019

Downloaded from pubs.acs.org on July 22, 2019

#### Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.

is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036

Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

# Chemically Cross-Linked Carbon Nanotube Films Engineered to Control Neuronal Signaling

Myriam Barrejón<sup>‡a</sup>, Rossana Rauti<sup>#b</sup>, Laura Ballerini<sup>\*b</sup> and Maurizio Prato<sup>\*a,c,d</sup>

<sup>a</sup>Department of Chemical and Pharmaceutical Sciences, Università degli Studi di

Trieste, Via Licio Giorgieri 1, Trieste 34127, Italy

<sup>b</sup>International School for Advanced Studies (SISSA/ISAS), Trieste 34136, Italy

°Carbon Bionanotechnology Group, CIC biomaGUNE, Paseo Miramón 182, San

Sebastián, 20014 Guipúzcoa, Spain

<sup>a</sup>Basque Foundation for Science, Ikerbasque, Bilbao 48013, Spain

#### ABSTRACT

In recent years, the use of free-standing carbon nanotube (CNT) films for neural tissue-engineering have attracted tremendous attention. CNT films show large surface area and high electrical conductivity that combined to flexibility and biocompatibility may promote neuron growth and differentiation while stimulating neural activity. Besides, adhesion, survival, and growth of neurons can be modulated through chemical modification of CNTs. Axonal and synaptic signaling can also be positively tuned by these materials. Here we describe the ability of free-standing CNT films to influence neuronal activity. We demonstrate that the degree of cross-linking between the CNTs has a strong impact on the electrical conductivity of the substrate, which, in turn, regulates neural circuit outputs.

**KEYWORDS**: single-walled carbon nanotube, cross-linking, functionalization degree, neuronal behavior, synaptic activity.

#### ACS Nano

Carbon nanotubes (CNTs) have long been recognized for owning the perfect combination of strength and conductivity, both thermal and electrical, along with large specific surface area characterized by low density.<sup>1,2</sup> However, in general CNTs are not suitable for practical applications, since they are produced in powder and show poor processability for use in the macroscopic scale. In this sense, the research on CNT films (often called buckypapers) has blossomed during the past years,<sup>3–6</sup> yielding materials with improved properties. Films of pure CNTs can be prepared by vacuum filtration methods,<sup>4</sup> however the mechanical performance and stability of pristine CNT films are still limited, as the interaction between adjacent CNTs takes place through weak  $\pi$ - $\pi$  stacking and van der Waals forces.<sup>7</sup> Chemical cross-linking of CNTs is a promising strategy for increasing the mechanical features and overcoming the aforementioned weaknesses of CNT films. A buckypaper made by covalently cross-linked CNTs would result in stronger interactions among CNTs featuring higher tensile strength of the CNTs films.<sup>6,8,9</sup> In addition, networks of CNTs generated by cross-linking are expected to exhibit interesting porous structure, beneficial for a wide number of applications.

Nowadays, chemical modification and assembly of CNTs into higher order constructs preserving CNTs founding features is still a major challenge. The cross-linking process is obtained, in general, at the expense of a reduction in electrical conductivity, due, at least in part, to the disruption of the CNT structure *via* covalent bonding. Therefore, a compromise between the mechanical and electrical properties may be necessary, and the optimal crosslinking degree should be determined according to the desired final properties and applications.

Several methods have been proposed for cross-linking CNTs, including the use of long and flexible poly-ethylene glycol chains,<sup>10</sup> 1,4-benzoquinones,<sup>11</sup> aryl diazonium salts<sup>12</sup> and polymer coating.<sup>13</sup> More recently, Ku *et al.* demonstrated, through molecular dynamics and experimental studies, that the mechanical properties strongly depend on the degree of cross-linking, length of cross-linkers and the diameter of the employed CNTs<sup>14</sup> and they proved that the incorporation of aromatic cross-linkers between carbon nanotube fibers, enhances the mechanical properties without a significant loss of electrical conductivity. Hence, this method appears as a

ACS Nano

promising methodology for the preparation of CNT films with interesting structural and electrical properties for a wide number of applications.

Among the potential applications of CNT films,<sup>15</sup> an emerging field is that of neuroscience. CNT substrates promote cell viability and adhesion<sup>16</sup> and during the last decade many studies reported that CNTs enhance and guide axon growth and to potentiate synapse formation and network activity<sup>16–22</sup> as well as single neuron excitability, by providing a cell-substrate electrical coupling.<sup>17</sup> When used to coat brain implants, CNTs are able to outperform the traditional electrodes by enhancing recordings and stimulation from and to brain tissues, both *in vitro* and *in vivo*.<sup>23,24</sup> Interestingly, CNTs films contribute in reducing astrogliosis, affecting astrocytes morphology and proliferation,<sup>21</sup> ultimately limiting glial scar formation.<sup>22</sup>

To successfully promote neuronal growth, the CNT substrates should show high mechanical stability in order to provide a stable neural interface.<sup>16</sup> High electrical conductivity is also crucial to achieve good stimulation of the neural cells.<sup>16</sup> However, the development of CNT substrates with appropriate mechanical stability and good conductivity, applicable to the design of neuro-implantable devices, still remains a

challenge. In this direction, the chemical modification of CNTs can be used to

influence the CNT/neuronal interaction and modify cell behavior.<sup>25</sup> Most of the studies involving neural substrates that consist of covalently modified CNTs reported so far, are based on oxidized materials.<sup>26-30</sup> CNTs covalently functionalized with protein growth factors have been also described.<sup>31</sup> Conducting polymers have been also used for the chemical modification of carbon nanotubes and their application for neuronal growth.<sup>32–34</sup> However, this kind of hybrid materials normally shows reduced electrical conductivity, a CNT feature shown to be relevant in neuronal interfacing.<sup>17,35,36</sup> In other cases, patterned CNTs are used as scaffolds to support the neurite outgrowth,<sup>37</sup> yielding fragile substrates that may lead to detachment of the CNTs during the implantation process exposing scaffolds materials potentially toxic.

In this framework, one of the major requirements to allow successful design of CNT-based devices in neurology, is the development of conductive and freestanding structures with high CNT content, covalently cross-linked materials with improved mechanical stability. Such freestanding CNT substrates could be simultaneously Page 7 of 58

 ACS Nano

used to deliver controlled and precise electrical stimulus and to promote cell growth on a physical template of controlled porosity.

Herein we focus on the chemical cross-linking of single-walled carbon nanotubes

(SWCNTs) through aromatic compounds, with the aim of achieving CNT substrates

with upgraded mechanical properties, still maintaining interesting electroconductive

behavior. We challenged the cross-linked SWCNT scaffolds, showing different

conductive properties, with neuronal networks growth and function.

#### RESULTS

#### Features of manufactured CNT-based substrates

Single-walled carbon nanotubes (SWCNTs) were chosen for the formation of the cross-linked materials because of their high flexibility, feature that could make the formation of the desired CNT meshes easier. Aryl diazonium salt chemistry, which has been widely used in the literature for grafting aryl groups to the surface of graphitic materials,<sup>38,39</sup> was applied for the cross-linking of SWCNTs. For this purpose, *p*-phenylene diamino derivatives with different lengths were employed as

cross-linkers, while the degree of entanglement was checked by varying the degree of functionalization. In detail, the crosslinking procedure was performed using *p*phenylenediamine, 2,5-diaminobenzenesulfonic acid and benzidine, yielding the products **ph-SWCNT**, **phSO<sub>3</sub>H-SWCNT**, **LCD-SWCNT** and **HCD-SWCNT**, respectively (Figure 1). **LCD** and **HCD** refer to the products resulting from the crosslinking with benzidine at low and high degrees of cross-linking, as reported in a previous work,<sup>40</sup> where the synthesis and characterization of **LCD-SWCNT** and **HCD-SWCNT** have been described.



Figure 1. Diazonium salt cross-linking reaction routes to provide the interlinked SWCNTs.

#### ACS Nano

The successful formation of the interlinked materials was followed by Raman spectroscopy, in combination with UV-Vis-NIR absorption spectroscopy, thermogravimetric analysis (TGA), atomic force microscopy (AFM), transmission electron microscopy (TEM), scanning electron microscopy (SEM) and conductivity measurements, to obtain fully detailed information about the structural, electronic and chemical properties of the synthesized nanohybrids.

UV-Vis-NIR absorption spectra were recorded for each material and compared with *p*-SWCNTs (Figure S1). The spectrum corresponding to *p*-SWCNTs exhibits the typical Van Hove singularities attributed to the different optical transitions. As expected, the cross-linking procedure resulted in the loss of the van Hove singularities. This loss of features is due to the alteration of the electronic structure, which is particularly indicative of side-wall functionalization.

Raman spectroscopy provided also efficient support to the successful cross-linking of SWCNTs (Figure S2 and Table 1). The spectra performed using the 785-nm line laser show the typical peaks corresponding to the CNTs, that is, the radial breathing mode (RBM), between 180 cm<sup>-1</sup> and 280 cm<sup>-1</sup>, and the two peaks corresponding to

the disorder-induced D mode and the C-C stretching G mode, at 1295 cm<sup>-1</sup> and 1595 cm<sup>-1</sup>, respectively. As observed, the intensity of the  $I_D/I_G$  ratio was higher for the cross-linked materials when compared to *p*-SWCNTs, as a consequence of the increase of the structural defects on the CNT sidewall after the cross-linking process. To get a deeper insight into the types of CNTs that were involved in the functionalization process (metallic or semiconducting) the RBM regions were analyzed. To this end, laser lines 532-nm and 633-nm were employed, since the 785-nm laser line is only in resonance with semiconducting CNTs. As shown in Figure S2d, where the RBM spectra are normalized to the mode of the nanotube with the largest diameter that was not affected by the functionalization (smallest Raman shift), the RBM intensities indicate that metallic CNTs are affected by the cross-linking process to a larger extend when compared to semiconducting CNTs. These results are in good agreement with previous studies that have revealed that the covalent functionalization of SWCNTs with diazonium salts takes place with high selectivity towards metallic CNTs.41,42

ACS Nano

The degree of functionalization was determined by TGA under nitrogen flow and consisted on heating ramps of 10°C/min up to 800°C (Figure S3 and Table 1). In order to facilitate the determination of the decomposition temperatures of the cross-linking agents, differential thermogravimetric (DTG) curves were superimposed (Figure S3).

From DTG curves, the initial decomposition temperatures of the weightlessness of the cross-linking agents were estimated as follows: around 280 °C for ph-SWCNT, 363 °C for phSO<sub>3</sub>H-SWCNT and 230 °C for LCD-SWCNTs and HCD-SWCNTs, and these are completely removed at around 600 °C, 580 °C and 380 °C for ph-SWCNT, phSO<sub>3</sub>H-SWCNT and LCD-/HCD- SWCNTs, respectively. The residual mass, once the cross-linking agents have been removed, is 68 % for ph-SWCNT, 78 % for phSO<sub>3</sub>H-SWCNT, 91 % for LCD-SWCNTs and 86 % for HCD-SWCNT, which might be attributed to remaining mass of CNTs, probably corresponding to those CNTs with larger diameters. TGA analysis allowed also the estimation of the functional group coverage (FGC) for each sample, that was estimated from the weight loss percentages (wt%) of the cross-linking agents (wt%-linker) and SWCNTs (wt%-SWCNTs) in each sample, and the molecular weights of the cross-linking agents (Mw<sub>-linker</sub>) and atomic mass of carbon according to the following equation:<sup>43</sup>

 $FCG = \frac{wt\%_{-SWCNTs}/12.01}{wt\%_{-linker}/Mw_{-linker}}$ 

For this purpose, the wt% was determined from the mass loss in the TGA curves under N<sub>2</sub>, at 600 °C for ph-SWCNT, at 550 °C for phSO<sub>3</sub>H-SWCNT, and 500 °C for LCD-SWCNTs and HCD-SWCNTs, where is considered that the cross-linking agent has been completely removed from the CNT sidewall. According to this, the TGA curves developed a group coverage of 1 group every 23 carbon atoms (2023 µmol/g) and 1 group every 77 carbon atoms (1045 µmol/g), for Ph-SWCNT and PhSO<sub>3</sub>H-SWCNT, respectively, in agreement with the results from the Raman studies presented above. For the longest linker consisting of two phenyl rings, the calculated group coverages were 1 group every 234 carbon atoms (536 µmol/g) and 1 group every 98 carbon atoms (944 µmol/g) for LCD-SWCNT and HCD-SWCNT, respectively, as previously described in the literature.<sup>40</sup> These latter results, along

ACS Nano

with the  $I_D/I_G$  values observed for both materials, confirmed the higher loading of linkers reached through the second round of functionalization.

Electrical conductivity studies were also performed for the synthesized materials and compared to those of *p*-SWCNTs. For this purpose, the van der Pauw method was employed.<sup>44</sup> Thin films were prepared using the vacuum filtration method and the average membrane thickness was measured. The sheet resistance (R<sub>s</sub>) was evaluated by means of a 4-point probe conductometer. For p-SWCNTs, Ph-SWCNT and PhSO<sub>3</sub>H-SWCNT, which did not show the free-standing structure required to be manipulated by tweezers, the conductivity was calculated without peeling off the materials from the surface of the PTFE filter. In order to avoid inaccurate reading due to the direct contact between the conductometer points and the filter, thick films of material were prepared. Electrical conductivity ( $\sigma$ ) was then calculated from the measured R<sub>s</sub> and the sample thickness (t), according to the formula  $\sigma = 1/(R_s t)$ . The data reported in Table 1 collects the results obtained from Raman, TGA and conductivity measurements. As expected, *p*-SWCNTs presented the highest values of conductivity which decreased after the disruption of the  $\pi$ - $\pi$  structure by means

of functionalization, and more so, with the increase of the functionalization degree, as clearly observed in the case of LCD-SWCNT relative to HCD-SWCNT. These results are consistent with the analysis previously performed on the RBM Raman regions (Figure S2d). The change toward less metallic behaviour after the crosslinking process explains the decrease of conductivity observed for the cross-linked materials that is higher when the loading of cross-linking agent increases.

Table 1.	TGA, Raman	and Conductivity	data for the	resulting cr	ross-linked materials
----------	------------	------------------	--------------	--------------	-----------------------

Material	TGA (µmol/g)*	Raman <i>I<sub>D</sub>/I<sub>G</sub></i>	σ (S/m)
<i>p</i> -SWCNTs	-	0.06	3389
Ph-SWCNT	2023	0.27	56
PhSO <sub>3</sub> H-SWCNT	1045	0.23	102
LCD-SWCNT	536	0.24	1083
HCD-SWCNT	944	0.39	81

\* µmol of functionalizing groups per gram of material.

To better understand the topography and structure of the cross-linked materials,

TEM and SEM studies were performed. TEM images revealed the existence of clear

differences before and after the interlinking process. For Ph-SWCNT and PhSO<sub>3</sub>H-

SWCNT (Figure S4), larger meshes of nanotubes were observed after the functionalization process, indicating a successful covalent cross-linking of the CNTs. Considerable differences were also observed by TEM between the LCD-SWCNT and HCD-SWCNT.<sup>40</sup> According to its paper-like physical appearance, the density of the meshwork was higher for LCD-SWCNTs in comparison with p-SWCNTs, and most notable, a dense meshwork of CNTs characterized by large surface roughness was observed for HCD-SWCNTs.<sup>40</sup> Similarly, a change in the surface morphology was observed by SEM between the *p*-SWCNTs and the interlinked materials. As observed, ph-SWCNT and phSO<sub>3</sub>H-SWCNT (Figure S5) exhibited a more compacted rough surface when compared to the *pristine* material. In the case of LCD-SWCNT and HCD-SWCNT, the interlinked SWCNTs exhibited a networklike structure with homogeneous distribution leading to a large continuous wrinkled film of nanotubes.40

To estimate the cross-linked SWCNTs potential as substrates for neuronal growth, dissociated hippocampal cultures<sup>35,45</sup> were seeded on LCD-SWCNTs and HCD-SWCNT. The choice of LCD-SWCNT and HCD-SWCNT for the study was motivated

by the easy preparation of free-standing substrates in these cases, which is a prerequisite for their future application as substrates for neural growth in the injured tissue. It is important to note that Ph-SWCNT and PhSO<sub>3</sub>H-SWCNT were obtained as powder samples after the functionalization process. Free-standing substrates were not achieved in these cases. Therefore, their manipulation in future implantation processes would not be a straightforward task. This, together with the fact that the electrical conductivity of Ph-SWCNT and PhSO<sub>3</sub>H-SWCNT was very similar to that of **HCD-SWCNT** (see Table 1), led us to the decision of using only LCD-SWCNT and HCD-SWCNT for neural interfacing. On the other hand, the existence of considerably different values of electrical conductivity between LCD-SWCNT and HCD-SWCNT (1083 S/m vs 81 S/m, respectively) allowed an interesting comparison about how this parameter affects neuronal behavior. These conductivity values are considerably better than those reported previously for MWCNTs chemically modified through the same approach,<sup>25</sup> which is probably attributable to the intrinsic conductivity of the *pristine* materials, that is much better in the case of the p-SWCNTs employed in the current work ( $\sigma$  = 3389 S/m for p-

#### ACS Nano

SWCNTs *vs.*  $\sigma$  = 625 S/m for *p*-MWCNTs (calculated from the sheet resistance in ref 25)). After the functionalization process, higher loading of functional groups is achieved in the present work (944 µmol/g for the SWCNTs with higher degree of functionalization *vs.* 230 µmol/g for the MWCNTs with higher degree of functionalization reported in ref. 25). Even so, the electrical conductivity for the functionalized SWCNTs is around 200 times better than that reported for the highly functionalized MWCNTs ( $\sigma$  = 0.341 S/m and  $\sigma$  = 81 S/m for functionalized-MWCNTs and SWCNTs, respectively), which suggest the promise of our cross-linked CNT-based substrates for the improvement of neuronal activity.

Confocal reconstructions and calcium imaging experiments were then performed to assess the behavior of the neural cells when seeded on the conductive CNT substrates.

Confocal reconstructions of hippocampal cultures interfaced to LCD-SWCNTs and HCD-SWCNTs substrates.

To investigate neuronal networks formation and growth when integrated with the SWCNTs films, we used rat dissociated hippocampal cultures.<sup>17,35,36</sup> Cultured biosystems allow reliable *in vitro* reconstruction of synaptic connections among heterogeneous neuronal phenotypes in the presence of neuroglial cells, and are brain-circuit models instrumental to investigate ad hoc manufactured materials for interfacing neuronal activity.

Primary neurons from rat hippocampus were plated on LCD- and HCD-SWCNTs films and, as control condition, on poly-L-ornithine treated glass slides. Cells were cultured into functional synaptic networks. Cell morphology and adhesion to SWCNTs substrates were assessed by immunofluorescence labeling and confocal microscopy. Figure 2A shows representative TEM images of the two different substrates. We compared neurons grown on poly-L-ornithine (Control) substrates with those grown on SWCNTs scaffolds, after 9-11 days *in vitro* (DIV). To prove the compatibility of both LCD- and HCD-SWCNTs substrates, we imaged by immunofluorescence the specific cytoskeletal components β-Tubulin III, to identify neurons, and glial fibrillary acidic protein (GFAP) for astrocytes.<sup>36,46,47</sup> In all cultures

1	
3	tested (s = 22 viewel fields for the three different conditions) before fivetion for
4	tested ( $n = 33$ visual fields for the three different conditions), before fixation for
5	
7	confocal microscopy, live neuronal calcium activity was monitored.
8	
9 10	
11	
12	
13 14	
15	
16	
17 18	
19	
20	
21 22	
23	
24	
25	
27	
28	
29	
30	
32	
33	
34 35	
36	
37	
38 39	
40	
41	
42 43	
44	
45	
46 47	
48	
49	
50 51	
52	
53	
54 55	
56	
57	
58 59	
60	ACS Paragon Plus Environment



*Figure 2.* In (A) TEM images for LCD-SWCNTs (left) and HCD-SWCNTs (right) substrates. In (B) confocal micrographs show hippocampal cultures grown (10 DIV) on Control (top), LCD-SWCNTs (middle) and HCD-SWCNTs (bottom) substrates immune-stained for  $\beta$  tubulin III (in red), GFAP (in green) and DAPI (blue) at lower (left panel) and higher magnification (right panel). Scale bar: 100 µm (left) and 50 µm (right).

Figure 2B shows low (left panels) and high (right panels) magnification confocal micrographs with β-Tubulin III positive cells (in red) and GFAP positive ones (in green) developed in control (top) or in the synthesized LCD-SWCNTs (middle) and HCD-SWCNTs (bottom) substrates; in all images nuclei are visualized by DAPI (in blue). TEM images for LCD- and HCD- SWCNTs are shown in A to provide further insight into the morphology of each substrate.

Both neurons and neuroglia cells matured once on SWCNTs supports, as shown in Fig 2B (high magnification) by the outgrowth of axons and dendrites in the case of neurons<sup>36,46</sup> and by the stellate shape of GFAP+ cells,<sup>36,48</sup> leading to the development of a complex network covering the entire SWCNTs surface. We further compared cell densities among LCD-SWCNTs, HCD-SWCNTs and control cultures. LCD- and HCD-SWCNTs and controls supported neuron and neuroglia growth in a similar manner, as highlighted by cell density measures (for neurons, in controls:

140 ± 35 β-tubulin positive cells/mm<sup>2</sup>; in LCD-SWCNTs: 110 ± 29 β-tubulin positive cells/mm<sup>2</sup>; in HCD-SWCNTs: 138 ± 35 β-tubulin positive cells/mm<sup>2</sup>; for neuroglia, in controls: 110 ± 20 GFAP positive cells/mm<sup>2</sup>; in LCD-SWCNTs: 120 ± 25 GFAP positive cells/mm<sup>2</sup>; in HCD-SWCNTs: 118 ± 20 GFAP positive cells/mm<sup>2</sup>; n = 11 visual fields per condition, three independent culture series). Thus, both LCD- and HCD-SWCNTs membranes allowed attachment and growth of rat hippocampal neurons displaying mature morphology.

Live imaging of hippocampal cultures interfaced to LCD-SWCNTs and HCD-SWCNTs substrates.

To study the emergence of neuronal activity by the networks formed interfaced to **LCD-SWCNTs** and **HCD-SWCNTs** substrates, we used fluorescent calcium imaging.<sup>49,50</sup> After 8-10 DIV, neurons mature and generate synaptic signaling spontaneously, involving the activation of glutamate and GABA<sub>A</sub> receptor mediated synapses,<sup>45,51</sup> the major central nervous system (CNS) neurotransmitters for fast synaptic communication. We compared activity emerging from neurons, cultured on

Control, LCD- and HCD-SWCNTs substrates (Figures 3 and 4). Neurons loaded with the membrane permeable  $Ca^{2+}$  dye Oregon green 488 BAPTA-1 were simultaneously visualized within the sampled area and on average 20 ± 4 fluorescent cells were analyzed in each visual field (680 × 680  $\mu$ m<sup>2</sup>; Fig. 3A and 4A, left panels).





*Figure 3.* In (A) (left) snapshots of representative fields of neuronal cultures grown on Control (top) and LCD-SWCNTs (bottom) substrates, stained with the Oregon Green 488-BAPTA-1 AM. Scale bar: 50 μm. In (A) (right) repetitive Ca<sup>2+</sup>-events spontaneously (top) or bicuculline

induced (bottom) recorded in hippocampal cultures of 10 DIV. In (B) cumulative distribution of IEI values recorded in saline solution of Control (black) and LCD (red) cells (\*\*\* p < 0.0001; Kolmogorov-Smirnoff test). In (C) cumulative distribution of bicuculline-induced IEI values of Control (black) and LCD (red) cells (\*\*\*= p< 0.0001; Kolmogorov-Smirnoff test).

A





20 s

**Figure 4**. In (A) (left) snapshots of representative fields of neuronal cultures grown on Control (top) and HCD-SWCNTs (bottom) substrates, stained with the Oregon Green 488-BAPTA-1 AM. Scale bar: 50  $\mu$ m. In (A) (right) repetitive Ca<sup>2+</sup>-events spontaneously (top) or bicuculline induced (bottom) recorded in hippocampal cultures of 10 DIV. In (B) cumulative distribution of IEI values recorded in saline solution of Control (black) and HCD (blue) cells (\*\*\* p < 0.0001; Kolmogorov-Smirnoff test). In (C) cumulative distribution of bicucullineinduced IEI values of Control (black) and HCD (blue) cells (\*\*\* p < 0.0001; Kolmogorov-Smirnoff test).

The experiments were performed at 9-11 DIV when neurons, intensely connected

by synapses, display spontaneous activity in the form of bursts of activity, emerging by irregular synchronized firing events,<sup>17,36,52</sup> generating transient episodes of calcium rise from the baseline (Figures 3 and 4).<sup>36,52–54</sup> In Control, spontaneous Ca<sup>2+</sup> activity was detected in 67 % of the recorded neurons (172 out of 257 neurons), visualized in each field (n = 10 fields). Notably, in LCD-SWCNTs virtually all (> 98 %, 133 out of 136 neurons; n = 6 fields) were active and generated spontaneous, repetitive Ca<sup>2+</sup> episodes. In Figure 3A (right) shows examples of fluorescent recordings of active cells sampled from Control and LCD-SWCNTs substrates. Spontaneous episodes of activity appear as bursts of synaptic, action potential, dependent events and are blocked by application of tetrodotoxin (TTX, 1 µM; a toxin Page 27 of 58

ACS Nano

that targets voltage dependent sodium channels). We measured the amount of Ca<sup>2+</sup>

episodes occurring in spontaneously active cells and we quantified the inter-event interval (IEI), the interval of time between the onset of a calcium wave and the beginning of the next one, that is significantly (\*\*\* p < 0.0001; Kolmogorov-Smirnoff test) shorter in LCD-SWCNTs substrates (on average 8 ± 4 s, n = 133 cells, from 3 different series of cultures) when compared to control ones (14 ± 4 s, n = 172 cells, from 3 different series of cultures; see the IEI cumulative distribution in Figure 3B), strongly indicative of a different functional organization due to the presence of LCD-SWCNTs.

In a second group of experiments we blocked inhibitory synaptic transmission by bicuculline (20  $\mu$ M) application. This antagonist of GABA<sub>A</sub> receptors is known to alter the profile of network activity<sup>55,56</sup> from random bursting to synchrony, characterized by more intense and regular bursting.<sup>53,54</sup> As shown in Figure 3A, active cells upon bicuculline exposure, generate Ca<sup>2+</sup> events with IEI of, on average, 4 ± 0.9 s in LCD-SWCNTs neurons (n = 133), a value significantly (p < 0.001) lower when compared to that of Control (on average 8 ± 3 s; n = 172 cells; see the cumulative distribution

plot in Figure 3C). Such disinhibited episodes were completely abolished by TTX applications, confirming their neuronal origin. Figure 4A (right panel) shows representative fluorescent tracings from active cells recorded in HCD-SWCNTs. notably  $Ca^{2+}$  spontaneous activity was detected only in 21 % (34 out of 162 neurons; **HCD-SWCNTs**) of the cells visualized in each field (n = 6 fields), a very low value when compared to their relative Control (65 %; 97 out of 149 neurons; n = 6 fields). When we measured the spontaneous  $Ca^{2+}$  activity, the IEI was significantly (\*\*\* p < 0.0001; Kolmogorov-Smirnoff test) longer in HCD-SWCNTs substrates (on average  $72 \pm 10$  s n = 34 cells, from 3 different series of cultures) when compared to control ones (on average  $17 \pm 7$  s, n = 97 cells, from 3 different series of cultures; see also cumulative distribution in Figure 4B). However, upon pharmacological removal of synaptic inhibition (Figure 4C) a IEI similar to control was restored (HCD-SWCNTs substrates on average  $8 \pm 5$  s, n = 34 cells; control substrates on average  $10 \pm 3$  s, n = 97 cells). Thus, apparently, the different substrates promote the formation of diverse networks, in particular the inhibitory control on HCD-SWCNTs appeared to be strongly developed in these cultured brain circuits, when compared to LCD-

**SWCNTs** and Control. While **LCD-SWCNTs**, as expected, boosted network activity in all network states (resting and disinhibited).

#### DISCUSSION

The present study provides important insight into how the electrical conductivity of the CNT free-standing substrates affects the growth and electrical properties of cultured hippocampal networks. The cross-linking of SWCNT with diaminophenyl derivatives has provided an efficient route to design free-standing CNT substrates with tunable electrical properties, promising for applications in neural tissue engineering. Raman and electrical studies demonstrated that the electrical conductivity of the final materials is directly related to the type of cross-linker and the degree of functionalization (Table 1). In the particular case of benzidine as crosslinker, an important decrease of the electrical conductivity was observed when increasing the degree of functionalization by 40 % (1083 S/m for LCD-SWCNT vs. 81 S/m for HCD-SWCNT), allowing the preparation of free-standing neuronal substrates with different electrical properties. Both, LCD-SWCNT and HCD-SWCNT,

have been employed as substrates for interfacing neural cells. The most important finding of the study is that neuronal circuits chronically interfaced to SWCNTs substrates can be effectively affected by the CNTs degree of functionalization. Cultured brain circuits represent the simplest *in vitro* model of brain network. The morphology and cell phenotype distribution of hippocampal networks did not differed when developed on control glass surfaces or on LCD- and HCD-SWCNTs carpets. The two cellular networks are made of healthy and functional cells, indicating the cytocompatibility of both SWCNTs substrates (Figure 2B).<sup>35</sup> Conversely, when investigating network dynamics by monitoring intracellular calcium activity, we observed significant differences comparing LCD-SWCNTs substrates with HCD ones. Live calcium episodes, whose neuronal and synaptic

nature was supported by TTX experiments,54 reflected the spontaneous activation of

synapses, typical of these preparations.<sup>17</sup> Specifically, such synchronized synaptic

activation are accepted measure of neural network dynamics.53

We speculated that LCD-SWCNTs substrates within their range of conductivity and functionalization could enhance neuronal activity (Figure 3), in a way similar to what happens with MWCNTs.<sup>17,25,35,57</sup> In fact, interfacing hippocampal neurons with **LCD-SWCNTs** substrates, we reproduced CNTs ability to support signaling and synchronization in cultured circuits.<sup>17,45</sup> Our results confirmed that neuronal physiological and synaptic efficacy could be tuned by specific neurons-surface interactions, in particular when using electrically conductive growth interfaces.<sup>25,35,36,58</sup>

We, in fact, observed that neurons grown on LCD-SWCNTs generate bursts with higher rate, with or without inhibition, potentially due to an improved efficiency in axonal signaling and to the increase in synaptic connections<sup>17,35,36,58</sup> (Figure 3). We favor the hypothesis that the LCD-SWCNTs ability to alter cellular excitability could significantly contribute to the described results. In fact, the higher the cellular excitability the higher would be the probability of finding active cells.<sup>36,59,60</sup>

As degree of functionalization increases, this effect on the emerging neuronal activity decreased (Figure 4). This effect is not attributable to differences in neuronal survival or morphology (Figure 3), but possibly represents a consequence of the

properties of the SWCNTs substrates and could primarily result from specific synaptic interactions.<sup>61</sup>

In fact, reducing the conductivity of the substrates, we observed a significant decrease in terms of active cells and the emerging spontaneous activity. We cannot exclude that HCD-SWCNTs interfere with the maturation of inhibitory neurons and the network composition. In this hypothesis, HCD-SWCNTs may favor more mature chloride ion fluxes through GABA<sub>A</sub> receptors. In neurons, the amplitude of the inhibitory currents is governed by the intracellular chloride concentration and, in more mature stages of development, goes from higher to lower values, in respect to the extracellular milieu.<sup>62</sup> Thus, in HCD-SWCNTs, there could be a higher fraction of effective inhibitory neurons, thus biasing the spontaneous network activity. Based on our results, we may propose that HCD-SWCNTs properties are responsible of a different maturation in cellular organization. However, even under these conditions, the block of GABA<sub>A</sub> receptor-mediated inhibition boosted Ca<sup>2+</sup> episodes as in control conditions, suggesting a similar role of inhibition in counteracting excitability in the synaptic network.

Page 33 of 58

#### ACS Nano

Hu and collaborators<sup>30</sup> found that the chemical functionalization of CNTs with different molecules is able to control the outgrowth and branching of neuronal processes. Accordingly, Malarkey and co-workers reported that SWCNT scaffolds with different conductivities affected rat hippocampal neuron neurite outgrowth.<sup>27</sup> Our current results are also in agreement with our recent report<sup>25</sup> where the impact of MWCNTs growth substrates on cell development and signaling depended on their degree of functionalization and on the functionalized groups. In that work,<sup>26</sup> despite the absence of changes in network size in all the functionalization conditions tested, we measured an increased synaptic activity only in those neurons interfaced to the MWCNTs with the lowest functionalization degree.

Although we cannot exclude such modulations, the simple tuning of neurite outgrowth would not explain the similar activity obtained in bicuculline when applied in control and **HCD-SWCNTs**, thus we favour the hypothesis that the conductivity of CNTs might regulate network excitability and synapse formation.<sup>17,35</sup> Overall, our results demonstrate that SWCNTs can be systematically manipulated

and functionalized to display different electrical properties.

These results show that SWCNTs structuring *via* cross-linking is a key factor to successfully use CNT-based substrates for biomedical applications or tissue engineering. For their peculiar chemical and electrical properties, as well as their functionalization degree, **LCD-SWCNTs** seem to be the most promising cross-linked substrate for the design of neuronal interfaces of the future.

Characterizing the interactions between CNTs and brain cells and their circuitry together with how the quality of conductivity affects their functionality offer developments for applying nanotechnology to and for the nervous system.

#### CONCLUSIONS

In this work, a facile and promising method based on chemical cross-linking of carbon nanotubes is employed for controlling the electrical conductivity of CNTbased substrates. We have developed a method to simultaneously obtain freestanding CNT-based substrates and tune the electrical properties of the final materials. Immunofluorescence studies and calcium imaging demonstrated that neural activity can be regulated by modifying the electrical properties of the CNT-

2	
ر ۸	
4	
5	
6	
7	
8	
0	
9	
10	
11	
12	
13	
11	
14	
15	
16	
17	
18	
10	
20	
20	
21	
22	
23	
2-J 74	
24	
25	
26	
27	
28	
20	
29	
30	
31	
32	
33	
3/	
24	
35	
36	
37	
38	
20	
29	
40	
41	
42	
43	
Δ <i>Λ</i>	
44	
45	
46	
47	
48	
⊿0	
77	
50	
51	
52	
53	
51	
54	
55	
56	
57	
58	
59	

60

based substrates, while maintaining neuronal growth unaffected. These findings may provide possibilities for controlling the electrical properties of future implantable neuronal interfaces.

## EXPERIMENTAL SECTION

#### **Materials**

All the chemicals and solvents were purchased from Sigma Aldrich and used without any further purification. Single-walled carbon nanotubes HiPco (SWCNTs) were purchased from Nanointegris (purified grade, length = 100-1000 nm, diameter ~0.8-1.2 nm, < 15% remaining iron particles) and used without further purification

## treatment.

## **Synthesis**

General procedure for the synthesis of cross-linked SWCNTs.

100 mg of *pristine* single walled carbon nanotubes (*p*-SWCNTs) were dispersed in 150 mL of *N*-methyl-2-pyrrolidone (NMP) and sonicated for 15 minutes. 100 mg of the corresponding phenyl derivative and 0.5 mL of isopentyl nitrite were added and the reaction mixture was stirred for 24 hours at 80°C. The crude was filtered through a PTFE membrane with an average pore size of 0.45 µm and the black precipitate was washed several times with NMP, methanol and diethyl ether. The resulting material was dried under vacuum and weighed.

#### Characterization methods

UV-Vis-NIR measurements were carried out on a Cary 5000 Spectrometer (Varian), using 1 cm path quartz cuvettes. Thermogravimetric analyses were performed using a TGA Q500 (TA Instruments). Raman spectra were obtained on Renishaw inVia Raman microscope at room temperature with an exciting laser source ( $\lambda$  = 785 cm<sup>-1</sup>). Measurements were taken with 10 s of exposure time and the laser spot was focused on the sample surface using a long working distance 50× objective. Raman spectra were collected on numerous spots on the sample and recorded with a Philips SPC1030NC camera. Atomic force microcopy (AFM) images were acquired in tapping mode using a Multimode V7.30 (Veeco Instruments Inc., Santa Barbara, USA) with a NanoScope V controller (Digital Instruments, Santa

Page 37 of 58

#### ACS Nano

Barbara, USA). The cantilevers (HQ:NSC15/AI BS probes from Mikromasch) were silicon cantilevers with a resonance frequency of 325 kHz and a nominal force constant of 40 Nm<sup>-1</sup>. The images were processed using WSxM (freely downloadable scanning probe microscopy software from (www.nanotec.es). Transmission electron microscopy (TEM) images were recorded on on a Philips EM208 TEM using iTEM software (Olympus Soft Imaging Solutions GmbH, Münster, Germany). About 1 mg of material was dispersed in 5 mL of EtOH and sonicated for 30 minutes. Then one drop of this solution was deposited on a TEM grid (Lacey carbon Film, Copper, 300 Mesh). Scanning electron microscopy (SEM) images were acquired collecting secondary electrons on a commercial SEM (Gemini SUPRA 40, Carl Zeiss NTS GmbH, Oberkochen). For the analysis, the different materials were placed on conductive double side carbon tape (Ted Pella, Inc., USA) and imaged at 5 keV. For the powdered samples (ph-SWCNT and phSO<sub>3</sub>H-SWCNT), about 1 mg of material was placed on the double-sided carbon tape previously attached to the SEM stub, and was pressed lightly to have the sample adhere to the tape. In the case of LCDand HCD-SWCNTs a piece of material was sectioned using a scalpel and mounted

on the SEM stub using the mentioned double sided carbon tape. Resistance was collected using a Jandel four-point probe analyzer (RM-3000) and conductivity was calculated applying the Ohm's law. For this purpose, the required films were prepared through filtration of 1 mg of material on a PTFE filter (Millipore 0.45 μm pores) and the membrane thickness was measured with a micrometer (High-Accuracy Digimatic Micrometer 293-100, Mitutoyo).

#### Preparation of primary hippocampal cultures.

Primary dissociated cultures were prepared from postnatal (P2-P3) rats as previously reported.<sup>17,30,42</sup> All procedures were approved by the local veterinary authorities and performed in accordance with the Italian law (decree 116/92) and the EU guidelines (86/609/CE, 2007/526/CE and 2010/63/UE). Animal's use was approved by the Italian Ministry of Health. All efforts were made to minimize animal suffering and to reduce the number of animals used. Cells were plated on poly-Lornithine-coated glass coverslips, on HCD-SWCNTs and on LCD-SWCNTs carpets. Before using for culturing, both SWCNTs substrates were mounted on the glass

coverslips (12×24 mm<sup>2</sup>, 0.13–0.16 mm thick, Kindler, EU) by a thin adhesive layer of PDMS cured at 120 °C. One hour prior to plating, CNTs substrates were treated with an air-plasma-cleaner in order to facilitate cell adhesion<sup>36,63</sup> and at the end sterilized with an UV lamp.

#### Calcium Imaging.

Cultures were loaded with cell permeable Ca<sup>2\*</sup>-dye Oregon Green 488 BAPTA-1 AM (Invitrogen). 4 mM stock solution of the Ca<sup>2\*</sup> dye was prepared in DMSO and cultures were incubated with a final concentration of 4 µM for 40 min (37 °C; 5% CO<sub>2</sub>).<sup>30,42</sup> The samples were then placed in a recording chamber mounted on an inverted microscope (Nikon Eclipse Ti-U) where they were continuously superfused at RT by a recording solution of the following composition (mM): 150 NaCl, 4 KCl, 1 MgCl<sub>2</sub>, 2 CaCl<sub>2</sub>, 10 HEPES, 10 glucose (pH adjusted to 7.4 with NaOH), to continuously supply nutrients to the tissue. Cultures were observed with a 20× objective (0.45 NA) and recordings were performed from visual fields (680 × 680

 $\mu$ m<sup>2</sup>, binning 4). Ca<sup>2+</sup>-dye was excited at 488 nm with a mercury lamp; excitation light was separated from the light emitted from the sample using a 395 nm dichroic mirror and ND filter (1/32). Images were continuously acquired (exposure time 150 ms) using an ORCA-Flash4.0 V2 sCMOS camera (Hamamatsu). The imaging system was controlled by an integrating imaging software (HCImage Live). In order to induce rhythmic burst, 20 µM bicuculline methiodide was bath-applied after 10 minutes recording. At the end of each experiment, Tetrodotoxin (TTX, 1µM, a voltage-gated, fast Na<sup>+</sup> channel blocker; Latoxan) was applied to confirm the neuronal nature of the recorded signals. Recorded images were analyzed off-line both with Fiji (selecting region of interest, ROI, around cell bodies) and Clampfit software (pClamp suite, 10.2 version; Molecular Devices LLC, US). Intracellular Ca<sup>2+</sup> transients were expressed as fractional amplitude increase ( $\Delta F/F_0$ , where  $F_0$  is the baseline fluorescence level and  $\Delta F$  is the rise over baseline); we determine the onset time of neuronal activation by detecting those events in the fluorescence signal that exceed at least five times the standard deviation of the noise.

Immunocytochemistry and image processing.

After 9-11 days *in-vitro* hippocampal neurons and glial cells were fixed by 4 % formaldehyde (prepared from fresh paraformaldehyde; Sigma) in PBS for 20 minutes, at room temperature (RT). After that, cells were washed three times with PBS and permeabilized with 1% Triton X-100 for 30 min, blocked with 5% FBS in PBS for 30 min at room temperature, and incubated with primary antibodies for 45 min. The primary antibodies used were as follows: rabbit polyclonal anti-β-tubulin III (1:500 dilution) and mouse monoclonal anti-GFAP (1:500 dilution). After PBS washes, cells were incubated for 45 minutes with AlexaFluor 594 goat anti-rabbit (Invitrogen, dilution 1:500) and AlexaFluor 488 goat anti-mouse (Invitrogen, dilution 1:500). Samples were mounted in Vectashield with DAPI in order to stain the nuclei (Vector Laboratories) on 1 mm tick coverslips. Images were acquired using a Nikon C2 confocal microscope (Nikon, Japan) at 40x magnification. Z-stacks were acquired every 500 nm, from seven to ten random fields for control and SWCNTs substrates. Offline analysis was performed using the image-processing package Fiji.

### ASSOCIATED CONTENT

The supporting information is available online: Figure S1. UV-Vis plots of the crosslinked materials in comparison with  $\rho$ -SWCNTs; Figure S2. Raman plots of the cross-linked materials in comparison with  $\rho$ -SWCNTs; Figure S3. TGA plots of the cross-linked materials in comparison with  $\rho$ -SWCNTs; Figure S4. TEM images of  $\rho$ -SWCNTs, ph-SWCNTs and phSO<sub>3</sub>H-SWCNTs; Figure S5. SEM images of  $\rho$ -SWCNTs, ph-SWCNTs and phSO<sub>3</sub>H-SWCNTs.

#### ACKNOWLEDGMENTS

This work was supported by the Spanish Ministry of Economy and Competitiveness MINECO (project CTQ2016-76721-R), by the University of Trieste, Consorzio Interuniversitario Nazionale per la Scienza e Tecnologia dei Materiali (INSTM), Ministero dell'Università e della Ricerca (MIUR) (FIRB prot. RBAP11ETKA and Cofin. Prot. 2010N3T9M4) and by the ByAxon n. 737116. MP, as the recipient of the AXA Chair, is grateful to the AXA Research Fund for financial support. This work

1		
2 3		n aufanna a' cuidea tha Maria da Maranto Haita, af Escallance, Duranna fuence tha
4	was	performed under the Maria de Maeztu Units of Excellence Program from the
5 6		
7	Spar	nish State Research Agency – Grant No. MDM-2017-0720
8		
10		
11	Auth	or Contributions.
12 13		
14	<sup>‡</sup> The	se authors contributed equally to this work.
15		
16 17		
18		
19	DEE	EDENCES
20 21	ΝĽΓ	ERENCES
22		
23	(1)	Hirsch, A. The Era of Carbon Allotropes, <i>Nat. Mater.</i> <b>2010</b> , <i>9</i> , 868–871.
24 25	(.)	
26		
27	(2)	Tasia D.: Tagmatarahia N.: Pianaa A.: Drata M. Chamiatay of Carbon
28 29	(2)	Tasis, D., Taginatarchis, N., Dianco, A., Frato, M. Chemistry of Carbon
30		
31		Nanotubes. <i>Chem. Rev.</i> 2006, <i>106</i> , 1105–1136.
32 33		
34		
35	(3)	Sreekumar, T. V.; Liu, T.; Kumar, S.; Ericson, L. M.; Hauge, R. H.; Smalley, R.
37	(-)	,,,,,,,
38		
39 40		E. Single-Wall Carbon Nanotube Films. <i>Chem. Mater.</i> 2003, <i>15</i> , 175–178.
40		
42		
43 44	(4)	Gu, B. H.; Swager, T. M. Fabrication of Free-Standing , Conductive , and
45		
46		Transportant Carbon Negatuba Filma Adv. Matar 0000 20 4422 4427
47 48		I ransparent Carbon Nanotube Films. Adv. Mater. 2008, 20, 4433–4437.
49		
50		
51 52	(5)	Zhang, L.; Zhang, G.; Liu, C.; Fan, S. High-Density Carbon Nanotube
53		
54		Buckypapers with Superior Transport and Mechanical Properties Nano Lett
55 56		Buskypupers with Superior transport and mechanical repetites. Nano Lett.
57		
58 50		
59		

ACS Nano

, *12*, 4848–4852.

- (6) Jakubinek, M. B.; Ashrafi, B.; Guan, J.; Johnson, M. B.; White, M. A.; Simard,
  - B. 3D Chemically Cross-Linked Single-Walled Carbon Nanotube Buckypapers. *RSC Adv.* **2014**, *4*, 57564–57573.
- Behabtu, N.; Green, M. J.; Pasquali, M. Carbon Nanotube-Based Neat Fibers.
   *Nano Today* 2008, *3*, 24–34.
- Yu, Q.; Alvarez, N. T.; Miller, P.; Malik, R.; Haase, M. R.; Schulz, M.; Shanov,
   V.; Zhu, X. Mechanical Strength Improvements of Carbon Nanotube Threads
   through Epoxy Cross-Linking. *Materials* 2016, *9*, 1–12.
- (9) Schirowski, M.; Abellán, G.; Nuin, E.; Pampel, J.; Dolle, C.; Wedler, V.; Fellinger, T. P.; Spiecker, E.; Hauke, F.; Hirsch, A. Fundamental Insights into the Reductive Covalent Cross-Linking of Single-Walled Carbon Nanotubes. *J.*

Am. Chem. Soc. 2018, 140, 3352–3360.

(10) Holzinger, M.; Steinmetz, J.; Samaille, D.; Glerup, M.; Paillet, M.; Bernier, P.;

2 3 4 5		Ley, L.; Graupner, R. [ 2 + 1 ] Cycloaddition for Cross-Linking SWCNTs.
6 7 8 9		<i>Carbon N. Y.</i> <b>2004</b> , <i>42</i> , 941–947.
10 11 12 13	11)	Ventura, D. N.; Stone, R. A.; Chen, K. S.; Hariri, H. H.; Riddle, K. A.; Fellers,
14 15 16		T. J.; Yun, C. S.; Strouse, G. F.; Kroto, H. W.; Acquah, S. F. A. Assembly of
17 18 19		Cross-Linked Multi-Walled Carbon Nanotube Mats. Carbon N. Y. 2010, 48,
20 21 22 23		987–994.
24 25 26 (* 27 28	12)	Kumar, R.; Rao, C. N. R. Assemblies of Single-Walled Carbon Nanotubes
29 30 31		Generated by Covalent Cross-Linking with Organic Linkers. J. Mater. Chem.
32 33 34 35		A <b>2015</b> , <i>3</i> , 6747–6750.
36 37 38 39	13)	Zhang, Y.; Broekhuis, A. A.; Stuart, M. C. A.; Fernandez, T.; Fausti, D.; Rudolf,
40 41 42		P.; Picchioni, F. Cross-Linking of Multiwalled Carbon Nanotubes with
43 44 45 46		Polymeric Amines. <i>Macromolecules</i> 2008, 6141–6146.
47 48 49 (* 50	14)	Park, O. K.; Choi, H.; Jeong, H.; Jung, Y.; Yu, J.; Lee, J. K.; Hwang, J. Y.; Kim,
51 52 53		S. M.; Jeong, Y.; Park, C. R.; Endo, M.; Ku, B. C. High-Modulus and Strength
54 55 56 57		Carbon Nanotube Fibers Using Molecular Cross-Linking. Carbon N. Y. 2017,
58 59 60		ACS Paragon Plus Environment

, 413–421.

- (15) Hu, L.; Hecht, D. S.; Gru, G. Carbon Nanotube Thin Films: Fabrication, Properties, and Applications. *Chem. Rev.* **2010**, *110*, 5790–5844.
- (16) Marchesan, S.; Ballerini, L.; Maurizio, P. Nanomaterials for Stimulating Nerve Growth. *Science* **2017**, *356*, 1010–1012.
- (17) Cellot, G.; Cilia, E.; Cipollone, S.; Rancic, V.; Sucapane, A.; Giordani, S.;
  Gambazzi, L.; Markram, H.; Grandolfo, M.; Scaini, D.; Gelain, F.; Casalis, L.;
  Prato, M.; Giugliano, M.; Ballerini, L. Carbon Nanotubes Might Improve
  Neuronal Performance by Favouring Electrical Shortcuts. *Nat. Nanotech.*2009, *4*, 126–133.
- (18) Bosi, S.; Fabbro, A.; Ballerini, L.; Prato, M. Carbon Nanotubes: A Promise for Nerve Tissue Engineering. *Nanotechnol. Rev.* 2013, *2*, 47–57.
- (19) Sucapane, A.; Cellot, G.; Prato, M.; Giugliano, M.; Parpura, V.; Ballerini, L.

Interactions Between Cultured Neurons and Carbon Nanotubes: A

	Nanoneuroscience Vignette. <i>J. Nanoneurosci.</i> 2009, <i>1</i> , 10–16.
(20)	Fan, L.; Feng, C.; Zhao, W.; Qian, L.; Wang, Y.; Li, Y. Directional Neurite
	Outgrowth on Superaligned Carbon Nanotube Yarn Patterned Substrate.
	<i>Nano Lett.</i> <b>2012</b> , <i>12</i> , 3668–3673.
(21)	Gottipati, M. K.; Samuelson, J. J.; Kalinina, I.; Bekyarova, E.; Haddon, R. C.;
	Parpura, V. Chemically Functionalized Single-Walled Carbon Nanotube Films
	Modulate the Morpho-Functional and Proliferative Characteristics of
	Astrocytes. <i>Nano Lett.</i> <b>2013</b> , <i>13</i> , 4387–4392.
(22)	Usmani, S.; Aurand, E. R.; Medelin, M.; Fabbro, A.; Scaini, D.; Laishram, J.;
	Rosselli, F. B.; Ansuini, A.; Zoccolan, D.; Scarselli, M.; Crescenzi, M. De; Bosi,
	S.; Prato, M.; Ballerini, L. 3D Meshes of Carbon Nanotubes Guide Functional
	Reconnection of Segregated Spinal Explants. Sci. Adv. 2016, 2, e1600087.
(23)	Keefer, E. W.; Botterman, B. R.; Romero, M. I.; Rossi, A. F.; Gross, G. W.
	Carbon Nanotube Coating Improves Neuronal Recordings Nat. Nanotech.
	<b>2008</b> , <i>3</i> , 1–6.

2	
3	
4	
5	
6	
0	
7	
8	
9	
10	
10	
11	
12	
13	
11	
14	
15	
16	
17	
18	
10	
19	
20	
21	
22	
25	
23	
24	
25	
26	
27	
27	
28	
29	
30	
31	
27	
32	
33	
34	
35	
20	
30	
37	
38	
39	
40	
40	
41	
42	
43	
11	
44	
45	
46	
47	
48	
40	
49	
50	
51	
50	
52	
53	
54	
55	
56	
57	
57	
58	
59	
60	

(24) Ansaldo, A.; Castagnola, E.; Maggiolini, E.; Fadiga, L.; Ricci, D. Superior Electrochemical Performance of Carbon Nanotubes Directly Grown on Sharp Microelectrodes. ACS Nano 2011, 5, 2206–2214.

- (25) Bosi, S.; Fabbro, A.; Cantarutti, C.; Mihajlovic, M.; Ballerini, L.; Prato, M. Carbon Based Substrates for Interfacing Neurons: Comparing Pristine with Functionalized Carbon Nanotubes Effects on Cultured Neuronal Networks. *Carbon N. Y.* **2016**, *97*, 87–91.
- (26) Hu, H.; Ni, Y.; Mandal, S. K.; Montana, V.; Zhao, B.; Haddon, R. C.; Parpura,

V. Polyethyleneimine Functionalized Single-Walled Carbon Nanotubes as a Substrate for Neuronal Growth. *J. Phys. Chem. B* **2005**, *109*, 4285–4289.

(27) Malarkey, E. B.; Fisher, K. A.; Bekyarova, E.; Liu, W.; Haddon, R. C.; Parpura,

V. Conductive Single-Walled Carbon Nanotube Substrates Modulate Neuronal Growth. *Nano Lett.* **2009**, *9*, 264–268.

(28) Liu, J.; Appaix, F.; Bibari, O.; Marchand, G.; Benabid, A. L.; Sauter-Starace,

F.; Waard, M. De. Control of Neuronal Network Organization by Chemical

ACS Nano

1 2	
- 3 4 5	Surface Functionalization of Multi-Walled Carbon Nanotube Arrays.
6 7 8	<i>Nanotechnology</i> <b>2011</b> , <i>22</i> , 195101.
9 10 11 (29) 13	Lee, H. J.; Yoon, O. J.; Kim, D. H.; Jang, Y. M.; Kim, H. W.; Lee, W. B.; Lee,
14 15 16	N. E.; Kim, S. S. Neurite Outgrowth on Nanocomposite Scaffolds Synthesized
17 18 19 20	from PLGA and Carboxylated Carbon Nanotubes. Adv. Eng. Mater. 2009, 11,
21 22 23	B261–B266.
24 25 26 (30) 27 28	Hu, H.; Ni, Y.; Montana, V.; Haddon, R. C.; Parpura, V. Chemically
29 30 31	Functionalized Carbon Nanotubes as Substrates for Neuronal Growth. Nano
32 33 34 35	<i>Lett.</i> <b>2004</b> , <i>4</i> , 14–16.
36 37 38 39	Matsumoto, K.; Sato, C.; Naka, Y.; Kitazawa, A.; Whitby, R. L. D.; Shimizu, N.
40 41 42	Neurite Outgrowths of Neurons with Neurotrophin-Coated Carbon Nanotubes.
43 44 45 46	<i>J. Biosci. Bioeng.</i> <b>2007</b> , <i>103</i> , 216–220.
47 48 49 (32) 50	Luo, X.; Weaver, C. L.; Zhou, D. D.; Greenberg, R.; Cui, X. T. Highly Stable
51 52 53	Carbon Nanotube Doped Poly(3,4-Ethylenedioxythiophene) for Chronic
54 55 56 57	Neural Stimulation. <i>Biomaterials</i> 2011, <i>32</i> , 5551–5557.
58 59 60	ACS Paragon Plus Environment

(33)	Abidian, M. R.; Ludwig, K. A.; Marzullo, T. C.; Martin, D. C.; Kipke, D. R. Interfacing Conducting Polymer Nanotubes with the Central Nervous System:
	Chronic Neural Recording Using Poly(3,4-Ethylenedioxythiophene)
	Nanotubes. <i>Adv. Mater.</i> <b>2009</b> , <i>21</i> , 3764–3770.
(34)	Alegret, N.; Dominguez-Alfaro, A.; González-Domínguez, J. M.; Arnaiz, B.;
	Cossío, U.; Bosi, S.; Vázquez, E.; Ramos-Cabrer, P.; Mecerreyes, D.; Prato,
	M. Three-Dimensional Conductive Scaffolds as Neural Prostheses Based on
	Carbon Nanotubes and Polypyrrole. ACS Appl. Mater. Interfaces 2018, 10,
	43904–43914.
(35)	Lovat, V.; Pantarotto, D.; Lagostena, L.; Cacciari, B.; Grandolfo, M.; Righi, M.;
	Spalluto, G.; Prato, M.; Ballerini, L. Carbon Nanotube Substrates Boost
	Neuronal Electrical Signaling. Nano Lett. 2005, 5, 1107–1110.
(36)	Bosi, S.; Rauti, R.; Laishram, J.; Turco, A.; Lonardoni, D.; Nieus, T.; Prato, M.;
	Scaini, D.; Ballerini, L. From 2D to 3D: Novel Nanostructured Scaffolds to
	Investigate Signalling in Reconstructed Neuronal Networks. Sci. Rep. 2015, 5,

ACS Paragon Plus Environment

1	
2	
3	
4	
5	
07	
/	
8	
9	
10	
17	
12	
14	
15	
16	
17	
18	
19	
20	
21	
22	
23	
24	
25	
26	
27	
28	
29	
30	
31	
32	
33	
34 25	
25	
27	
32	
30	
40	
41	
42	
43	
44	
45	
46	
47	
48	
49	
50	
51	
52	
53	
54	
55	
56	
57	
58	
59	
60	

(37) Jang, M. J.; Namgung, S.; Hong, S.; Nam, Y. Directional Neurite Growth Using Carbon Nanotube Patterned Substrates as a Biomimetic Cue. *Nanotechnology* 2010, *21*, 235102–235108.

- (38) Bahr, J. L.; Tour, J. M. Highly Functionalized Carbon Nanotubes Using *In Situ* Generated Diazonium Compounds. *Chem. Mater.* **2001**, *13*, 3823–3824.
- (39) Bahr, J. L.; Yang, J.; Kosynkin, D. V; Bronikowski, M. J.; Smalley, R. E.; Tour,
   J. M. Functionalization of Carbon Nanotubes by Electrochemical Reduction of
   Aryl Diazonium Salts : A Bucky Paper Electrode. *J. Am. Chem. Soc* 2001, 123,

6536-6542.

9562.

(40) Barrejón, M.; Syrgiannis, Z.; Burian, M.; Bosi, S.; Fornasiero, P.; Amenitsch,

H.; Prato, M. Cross-Linked Carbon Nanotube Adsorbents for Water Treatment : Tuning the Sorption Capacity through Chemical Functionalization. *ACS Appl. Mater. Interfaces* **2019**, *11*, 12920-12930.

- (41) Dyke, A.; Stewart, M. P.; Maya, F.; Tour, J. M. Diazonium-Based Functionalization of Carbon Nanotubes: XPS and GC–MS Analysis and Mechanistic Implications. *Synlett* 2004, 155–160.
- Schirowski, M.; Tyborsky, C.; Janina, M.; Hauke, F.; Hirsch, A.; Goclon, J.
   Reductive Diazotation of Carbon Nanotubes: An Experimental and Theoretical Selectivity Study. *Chem. Sci.* 2019, *10*, 706–717.
- (43) Maeda, Y.; Saito, K.; Akamatsu, N.; Chiba, Y.; Ohno, S.; Okui, Y.; Yamada, M.; Hasegawa, T.; Kako, M.; Akasaka, T. Analysis of Functionalization Degree of Single-Walled Carbon Nanotubes Having Various Substituents. *J. Am. Chem. Soc.* 2012, *134*, 18101–18108.
- (44) L. J. van der Pauw. A Method of Measuring the Resistivity and Hall Coefficient on Lamellae of Aarbitrary Shape. *Phys. Tech. Rev.* **1958**, *20*, 220–224.
- (45) Cellot, G.; Toma, F. M.; Kasap Varley, Z.; Laishram, J.; Villari, A.; Quintana,
   M.; Cipollone, S.; Prato, M.; Ballerini, L. Carbon Nanotube Scaffolds Tune
   Synaptic Strength in Cultured Neural Circuits: Novel Frontiers in

ACS Nano

2 3 4 5 6		Nanomaterial-Tissue Interactions. J. Neurosci. 2011, 31, 12945–12953.
7 8 9	(46)	Alfred, C.; Banker, G. A.; Binder, L. Immunocytochemical Localization of
10 11 12 13		Tubulin and Protein 2 During the Development Hippocampal Neurons in
14 15 16 17		Culture. <i>J. Neurosci.</i> 1986, <i>6</i> , 714–722.
18 19 20 21	(47)	Willmott, N. J.; Wong, K.; Strong, A. J. Intercellular Ca+2 Waves in Rat
22 23 24		Hippocampal Slice and Dissociated Glial ^ Neuron Cultures Mediated by Nitric
25 26 27 28		Oxide. FEBS Lett. 2000, 487, 239–247.
29 30 31 32	(48)	Marconi, E.; Nieus, T.; Maccione, A.; Valente, P.; Simi, A.; Messa, M.; Dante,
33 34 35		S.; Baldelli, P.; Berdondini, L.; Benfenati, F. Emergent Functional Properties
36 37 38 39		of Neuronal Networks with Controlled Topology. PLoS One 2012, 7, e34648.
40 41 42 43	(49)	Ross, W. N.; Hole, W. Understanding Calcium Waves and Sparks in Central
44 45 46 47		Neurons. Nat. Rev. Neuoscience 2015, 13, 157–168.
48 49 50	(50)	Grienberger, C.; Konnerth, A. Primer Imaging Calcium in Neurons. Neuron
51 52 53 54 55 56 57 58		<b>2012</b> , <i>73</i> , 862–885.
59		

2
R
1
4
5
6
7
8
9
10
11
11
12
13
14
15
16
17
18
10
17
20
21
22
23
24
25
26
20
27
28
29
30
31
32
33
34
35
20
30
37
38
39
40
41
42
<u>4</u> 2
7-J // /
44
45
46
47
48
49
50
51
57
52
22
54
55
56
57
58
59
60
50

(51) Galante, M.; Nistri, A.; Ballerini, L. Opposite Changes in Synaptic Activity of Organotypic Rat Spinal Cord Cultures after Chronic Block of AMPAÏkainate or Glycine and GABA A Receptors. *J. Physiol.* 2000, *523*, 639–651.

(52) Rauti, R.; Lozano, N.; León, V.; Scaini, D.; Musto, M.; Rago, I.; Paolo, F.;
Severino, U.; Fabbro, A.; Vázquez, E.; Kostarelos, K.; Prato, M.; Ballerini, L.
Graphene Oxide Nanosheets Reshape Synaptic Function in Cultured Brain
Networks. *ACS Nano* 2016, *10*, 4459–4471.

- (53) Stetter, O.; Battaglia, D.; Soriano, J.; Geisel, T. Model-Free Reconstruction of Excitatory Neuronal Connectivity from Calcium Imaging Signals. *PLOS Comput. Biol.* 2012, *8*, e1002653.
- (54) Fabbro, A.; Pastore, B.; Nistri, A.; Ballerini, L. Activity-Independent Intracellular Ca<sup>2+</sup> Oscillations Are Spontaneously Generated by Ventral Spinal Neurons during Development *In Vitro. Cell Calcium* **2007**, *41*, 317–329.
- (55) Sokal, D. M.; Mason, R.; Parker, T. L. Multi-Neuronal Recordings Reveal a Differential Effect of Thapsigargin on Bicuculline- or Gabazine-Induced

ACS Nano

55 of 58		ACS Nano
		Epileptiform Excitability in Rat Hippocampal Neuronal Networks. <i>Neuropharmacology</i> <b>2000</b> , <i>39</i> , 2408–2417.
	(56)	Tibau, E.; Valencia, M.; Soriano, J. Identification of Neuronal Network
		Properties from the Spectral Analysis of Calcium Imaging Signals in Neuronal
		Cultures. Front. Neural Circuits 2013, 7, 1–16.
	(57)	Mazzatenta, A.; Giugliano, M.; Campidelli, S.; Gambazzi, L.; Businaro, L.;
		Markram, H.; Prato, M.; Ballerini, L. Interfacing Neurons with Carbon
		Nanotubes: Electrical Signal Transfer and Synaptic Stimulation in Cultured
		Brain Circuits. <i>J. Neurosci.</i> 2007, <i>27</i> , 6931–6936.
	(58)	Schmidt, C. E.; Shastri, V. R.; Vacanti, J. P.; Anger, R. O. L. Stimulation of
		Neurite Outgrowth Using an Electrically. <i>Proc. Natl. Acad. Sci.</i> 1997, <i>94</i> , 8948–
		8953.
	(59)	Aguado, F.; Carmona, M. A.; Pozas, E.; Aguiló, A.; Martínez-guijarro, F. J.;
		Alcantara, S.; Borrell, V.; Yuste, R.; Ibañez, C. F.; Soriano, E. BDNF Regulates
		Spontaneous Correlated Activity at Early Developmental Stages by Increasing

2	
3	
4	
5	
6	
7	
8	
å	
10	
10	
11	
12	
13	
14	
15	
16	
17	
18	
10	
עו רכ	
20	
21	
22	
23	
24	
25	
26	
27	
27	
20	
29	
30	
31	
32	
33	
34	
35	
36	
37	
20	
38	
39	
40	
41	
42	
43	
44	
45	
46	
Δ7	
т/ ЛО	
40	
49	
50	
51	
52	
53	
54	
55	
56	
57	
57	
58	
59	

1

Synaptogenesis and Expression of the K<sup>+</sup> / Cl<sup>-</sup> Co-Transporter KCC2. *Development* **2003**, 1267–1280.

## Yang, L.; Qi, Y.; Yang, Y. Astrocytes Control Food Intake by Inhibiting AGRP Neuron Activity *via* Adenosine A<sub>1</sub> Receptors. *Cell Rep.* 2015, *11*, 798–807.

- (61) Marom, S.; Shahaf, G. Development , Learning and Memory in Large Random Networks of Cortical Neurons : Lessons beyond Anatomy. *Q. Rev. Biophys.* 2002, *35*, 63–87.
- (62) Arosio, D.; Ratto, G. M. Twenty Years of Fluorescence Imaging of Intracellular
   Chloride. *Front. Cell. Neurosci.* 2014, *8*, 258.
- (63) Martín, C.; Merino, S.; González-Domínguez, J. M.; Rauti, R.; Ballerini, L.; Prato, M.; Vázquez, E. Graphene Improves the Biocompatibility of Polyacrylamide Hydrogels: 3D Polymeric Scaffolds for Neuronal Growth. *Sci.*

*Rep.* **2017**, *7*, 10942.





176x105mm (149 x 149 DPI)

ACS Paragon Plus Environment